



Total Quality. Assured.

TEST REPORT



中国认可
国际互认
检测
TESTING
CNAS L0220

Number: GZHT91213670

Date: Oct 18, 2023

Applicant: NANJING MINGXIN REFLECTIVE MATERIALS CO.
,LTD.
2ND FLOOR, BUILDING 6, CHINA
OVERSEAS ZHIHUI PORT, NO. 1111,
FUYING ROAD, CHUNHUA STREET, JIANGNING
DISTRICT, NANJING CHINA
Attn: ZHANG QIANG

Sample Description:

One (1) piece of submitted sample said to be 5cm Reflective tape for pressing (PET).

Standard : BS EN ISO 20471:2013+A1:2016
Colour : Gray
Style No./Name : MX-LRN03
Manufacturer : Nanjing Mingxin Reflective Materials. Co. Ltd.
Country Of Original : China
Date Received/Date Test Started: Sep 11, 2023
Date Final Information Confirmed/ Oct 18, 2023/--
Date Payment Received:

Test Result Please Refer To Attached Page(S).

Should you have any query on this report, you may contact at gzfootwear@intertek.com

Authorized By:
For Intertek Testing Services Shenzhen Ltd.
Guangzhou Branch

Guiliang Dong
Senior Lab Manager



Page 1 Of 9

wx / lydiayang

Intertek Testing Services Shenzhen Ltd. Guangzhou Branch
深圳天祥质量技术服务有限公司广州分公司
Room 401/501/601/801/901/1003, No. 8, East BaoYing Road, Huangpu District, Guangzhou 510730
广州市黄埔区保盈东路8号401房、501房、601房、801房、901房、1003房
Tel: +86 20 2820 9114 Postcode: 510730

www.intertek.com

检验检测专用章

SHENZHEN BRANCH

(6)

1 Retroreflective Performance Of New Materials (Separate Performance Retroreflective Material)
(BS EN ISO 20471:2013+A1:2016, 6.1 & CIE 54.2:1982)

Coefficient Of Retroreflective Test Before Test Exposures:

x-Direction (Horizontal: $\epsilon=0^\circ$)				
Observation Angle	Entrance Angle β_1 ($\beta_2=0$)	Coefficient Of Retroreflection	Requirement	Pass/Fail
12'	5°	590 cd/(lx·m ²)	Min. 330 cd/(lx·m ²) (*)	Pass
12'	20°	604 cd/(lx·m ²)	Min. 290 cd/(lx·m ²) (*)	Pass
12'	30°	596 cd/(lx·m ²)	Min. 180 cd/(lx·m ²) (*)	Pass
12'	40°	550 cd/(lx·m ²)	Min. 65 cd/(lx·m ²) (*)	Pass
20'	5°	437 cd/(lx·m ²)	Min. 250 cd/(lx·m ²) (*)	Pass
20'	20°	446 cd/(lx·m ²)	Min. 200 cd/(lx·m ²) (*)	Pass
20'	30°	432 cd/(lx·m ²)	Min. 170 cd/(lx·m ²) (*)	Pass
20'	40°	420 cd/(lx·m ²)	Min. 60 cd/(lx·m ²) (*)	Pass
1°	5°	48.8 cd/(lx·m ²)	Min. 25 cd/(lx·m ²) (*)	Pass
1°	20°	49.0 cd/(lx·m ²)	Min. 15 cd/(lx·m ²) (*)	Pass
1°	30°	48.2 cd/(lx·m ²)	Min. 12 cd/(lx·m ²) (*)	Pass
1°	40°	40.4 cd/(lx·m ²)	Min. 10 cd/(lx·m ²) (*)	Pass
1° 30'	5°	32.4 cd/(lx·m ²)	Min. 10 cd/(lx·m ²) (*)	Pass
1° 30'	20°	32.3 cd/(lx·m ²)	Min. 7 cd/(lx·m ²) (*)	Pass
1° 30'	30°	31.7 cd/(lx·m ²)	Min. 5 cd/(lx·m ²) (*)	Pass
1° 30'	40°	30.9 cd/(lx·m ²)	Min. 4 cd/(lx·m ²) (*)	Pass

Retroreflective Performance Of New Materials (Separate Performance Retroreflective Material) (Cont)

y-Direction (Vertical: $\varepsilon=90^\circ$)				
Observation Angle	Entrance Angle β_1 ($\beta_2=0$)	Coefficient Of Retroreflection	Requirement	Pass/Fail
12'	5°	596 cd/(lx·m ²)	Min. 330 cd/(lx·m ²) (*)	Pass
12'	20°	612 cd/(lx·m ²)	Min. 290 cd/(lx·m ²) (*)	Pass
12'	30°	601 cd/(lx·m ²)	Min. 180 cd/(lx·m ²) (*)	Pass
12'	40°	554 cd/(lx·m ²)	Min. 65 cd/(lx·m ²) (*)	Pass
20'	5°	427 cd/(lx·m ²)	Min. 250 cd/(lx·m ²) (*)	Pass
20'	20°	442 cd/(lx·m ²)	Min. 200 cd/(lx·m ²) (*)	Pass
20'	30°	430 cd/(lx·m ²)	Min. 170 cd/(lx·m ²) (*)	Pass
20'	40°	408 cd/(lx·m ²)	Min. 60 cd/(lx·m ²) (*)	Pass
1°	5°	47.3 cd/(lx·m ²)	Min. 25 cd/(lx·m ²) (*)	Pass
1°	20°	50.2 cd/(lx·m ²)	Min. 15 cd/(lx·m ²) (*)	Pass
1°	30°	49.6 cd/(lx·m ²)	Min. 12 cd/(lx·m ²) (*)	Pass
1°	40°	40.5 cd/(lx·m ²)	Min. 10 cd/(lx·m ²) (*)	Pass
1° 30'	5°	32.4 cd/(lx·m ²)	Min. 10 cd/(lx·m ²) (*)	Pass
1° 30'	20°	33.9 cd/(lx·m ²)	Min. 7 cd/(lx·m ²) (*)	Pass
1° 30'	30°	33.1 cd/(lx·m ²)	Min. 5 cd/(lx·m ²) (*)	Pass
1° 30'	40°	31.1 cd/(lx·m ²)	Min. 4 cd/(lx·m ²) (*)	Pass

Remark: * = If A Sample Is Defined As Orientation Sensitive In Orientation Sensitive Check Test, The Coefficient Of Retroreflection Of This Material At One Of The Two Rotation Angles Shall Comply With The Minimum Requirement, The Coefficient Of Retroreflection At The Other Rotation Angle Shall Comply With Not Less Than 75% Of The Minimum Requirement.

Orientation Sensitive Check Test (For Original Material)			
Sample Direction	Observation Angle	Entrance Angle 5°	Comment
x-Direction [Horizontal]	12'	590 cd/(lx·m ²)	If The Difference Between The X And Y Values Is Less Than 15% The Sample Is Not Considered Orientation Sensitive.
y-Direction [Vertical]	12'	596 cd/(lx·m ²)	
Difference Between x & y Direction	6 cd/(lx·m ²)		
Difference Expressed As A Percentage (%)	1.0%		Non-sensitive

- 2 Retroreflection After Abrasion (BS EN ISO 20471:2013+A1:2016, 7.3 & ISO 12947-2:1998/Cor.1:2002, Pressure: 9 kPa, 5000 Cycles)

Test Exposure	Test Method
Abrasion	ISO 12947-2:1998/Cor.1:2002, Pressure: 9 kPa, 5000 Cycles

x-Direction (Horizontal: $\epsilon=0^\circ$)					
Material Type	Observation Angle	Entrance Angle β_1 ($\beta_2 = 0^\circ$)	Coefficient Of Retroreflection	Requirement	Pass/Fail
Retroreflective Material	12'	5°	573 cd/(lx·m ²)	Min. 100 cd/(lx·m ²) (*)	Pass

y-Direction (Vertical: $\epsilon=90^\circ$)					
Material Type	Observation Angle	Entrance Angle β_1 ($\beta_2 = 0^\circ$)	Coefficient Of Retroreflection	Requirement	Pass/Fail
Retroreflective Material	12'	5°	569 cd/(lx·m ²)	Min. 100 cd/(lx·m ²) (*)	Pass

Remark:

* = If A Sample Is Defined As Orientation Sensitive In Orientation Sensitive Check Test, The Coefficient Of Retroreflection Of This Material At One Of The Two Rotation Angles Shall Comply With The Minimum Requirement, The Coefficient Of Retroreflection At The Other Rotation Angle Shall Comply With Not Less Than 75% Of The Minimum Requirement.

3 Retroreflection After Flexing (BS EN ISO 20471:2013+A1:2016, 6.2 & 7.3 & ISO 7854:1995)

Test Exposure	Test Method
Flexing	ISO 7854:1995, Method A, 7500 Cycles

x-Direction (Horizontal: $\epsilon=0^\circ$)					
Material Type	Observation Angle	Entrance Angle β_1 ($\beta_2 = 0^\circ$)	Coefficient Of Retroreflection	Requirement	Pass/Fail
Retroreflective Material	12'	5°	494 cd/(lx·m ²)	Min. 100 cd/(lx·m ²) (*)	Pass

y-Direction (Vertical: $\epsilon=90^\circ$)					
Material Type	Observation Angle	Entrance Angle β_1 ($\beta_2 = 0^\circ$)	Coefficient Of Retroreflection	Requirement	Pass/Fail
Retroreflective Material	12'	5°	489 cd/(lx·m ²)	Min. 100 cd/(lx·m ²) (*)	Pass

Remark:

* = If A Sample Is Defined As Orientation Sensitive In Orientation Sensitive Check Test, The Coefficient Of Retroreflection Of This Material At One Of The Two Rotation Angles Shall Comply With The Minimum Requirement, The Coefficient Of Retroreflection At The Other Rotation Angle Shall Comply With Not Less Than 75% Of The Minimum Requirement.

4 Retroreflection After Folding At Cold Temperatures (BS EN ISO 20471:2013+A1:2016, 6.2 & 7.3 & ISO 4675:1990, $(-20 \pm 2)^\circ\text{C}$)

Test Exposure	Test Method
Folding At Cold Temperatures	ISO 4675:1990, $-20 \pm 2^\circ\text{C}$

x-Direction (Horizontal: $\epsilon=0^\circ$)					
Material Type	Observation Angle	Entrance angle β_1 ($\beta_2 = 0^\circ$)	Coefficient Of Retroreflection	Requirement	Pass/Fail
Retroreflective Material	12'	5°	544 cd/(lx·m ²)	Min. 100 cd/(lx·m ²) (*)	Pass

y-Direction (Vertical: $\epsilon=90^\circ$)					
Material Type	Observation Angle	Entrance angle β_1 ($\beta_2 = 0^\circ$)	Coefficient Of Retroreflection	Requirement	Pass/Fail
Retroreflective Material	12'	5°	538 cd/(lx·m ²)	Min. 100 cd/(lx·m ²) (*)	Pass

Remark:

* = If A Sample Is Defined As Orientation Sensitive In Orientation Sensitive Check Test, The Coefficient Of Retroreflection Of This Material At One Of The Two Rotation Angles Shall Comply With The Minimum Requirement, The Coefficient Of Retroreflection At The Other Rotation Angle Shall Comply With Not Less Than 75% Of The Minimum Requirement.

5 Retroreflection After Exposure To Temperature Variation (BS EN ISO 20471:2013+A1:2016, 6.2 & 7.3 & 7.4.4)

Test Exposure	Test Method
Temperature Variation	a) For 12 H At $(50 \pm 2)^{\circ}\text{C}$; Immediately Followed By b) 20 H At $-(30 \pm 2)^{\circ}\text{C}$; Immediately Followed By c) For At Least 2 H At $(20 \pm 2)^{\circ}\text{C}$ And $(65 \pm 5)\%$ Relative Humidity

x-Direction (Horizontal: $\varepsilon=0^{\circ}$)					
Material Type	Observation Angle	Entrance Angle β_1 ($\beta_2 = 0^{\circ}$)	Coefficient Of Retroreflection	Requirement	Pass/Fail
Retroreflective Material	12'	5°	570 cd/(lx·m ²)	Min. 100 cd/(lx·m ²) (*)	Pass

y-Direction (Vertical: $\varepsilon=90^{\circ}$)					
Material Type	Observation Angle	Entrance Angle β_1 ($\beta_2 = 0^{\circ}$)	Coefficient Of Retroreflection	Requirement	Pass/Fail
Retroreflective Material	12'	5°	559 cd/(lx·m ²)	Min. 100 cd/(lx·m ²) (*)	Pass

Remark:

* = If A Sample Is Defined As Orientation Sensitive In Orientation Sensitive Check Test, The Coefficient Of Retroreflection Of This Material At One Of The Two Rotation Angles Shall Comply With The Minimum Requirement, The Coefficient Of Retroreflection At The Other Rotation Angle Shall Comply With Not Less Than 75% Of The Minimum Requirement.

6 Retroreflection After Washing (BS EN ISO 20471:2013+A1:2016, 6.2 & 7.3 & 7.5.2)

Wash Condition:	
Washing Standard:	ISO 6330:2012
Machine:	Type A
Reagent:	Reference Detergent 3
Washing Procedure:	6N
Bleaching Procedure:	Do Not Bleach
Drying Procedure:	Tumble Drying Possible Normal Temperature; Exhaust Temperature Max. 80°C
Ironing Procedure:	Do Not Iron
Professional Textile Care Procedure:	Do Not Dry Clean
Number Of Cycles:	50

x-Direction (Horizontal: $\epsilon=0^\circ$)					
Material Type	Observation Angle	Entrance Angle β_1 ($\beta_2 = 0^\circ$)	Coefficient Of Retroreflection	Requirement	Pass/Fail
Retroreflective Material	12'	5°	316 cd/(lx·m ²)	Min. 100 cd/(lx·m ²) (*)	Pass

y-Direction (Vertical: $\epsilon=90^\circ$)					
Material Type	Observation Angle	Entrance Angle β_1 ($\beta_2 = 0^\circ$)	Coefficient Of Retroreflection	Requirement	Pass/Fail
Retroreflective Material	12'	5°	323 cd/(lx·m ²)	Min. 100 cd/(lx·m ²) (*)	Pass

Remark:

* = If A Sample Is Defined As Orientation Sensitive In Orientation Sensitive Check Test, The Coefficient Of Retroreflection Of This Material At One Of The Two Rotation Angles Shall Comply With The Minimum Requirement, The Coefficient Of Retroreflection At The Other Rotation Angle Shall Comply With Not Less Than 75% Of The Minimum Requirement.

7 Retroreflection After Rainfall (BS EN ISO 20471:2013+A1:2016, 7.3 & 7.4.5)

Test Exposure	Test Method
Rainfall	BS EN ISO 20471:2013+A1:2016, Annex C

x-Direction (Horizontal: $\epsilon=0^\circ$)					
Material Type	Observation Angle	Entrance Angle β_1 ($\beta_2 = 0^\circ$)	Coefficient Of Retroreflection	Requirement	Pass/Fail
Retroreflective Material	12'	5°	340 cd/(lx·m ²)	Min. 100 cd/(lx·m ²) (*)	Pass

y-Direction (Vertical: $\epsilon=90^\circ$)					
Material Type	Observation Angle	Entrance Angle β_1 ($\beta_2 = 0^\circ$)	Coefficient Of Retroreflection	Requirement	Pass/Fail
Retroreflective Material	12'	5°	359 cd/(lx·m ²)	Min. 100 cd/(lx·m ²) (*)	Pass

Remark:

* = If A Sample Is Defined As Orientation Sensitive In Orientation Sensitive Check Test, The Coefficient Of Retroreflection Of This Material At One Of The Two Rotation Angles Shall Comply With The Minimum Requirement, The Coefficient Of Retroreflection At The Other Rotation Angle Shall Comply With Not Less Than 75% Of The Minimum Requirement.



End Of Report

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct. No copy of the test report(except for full text copy) shall be made without the written approval by Intertek.

Remark:

1. As Requested by the Applicant, For Details Refer to Attached Page (s).
2. All the tested item are tested under the standard condition.
3. The report is valid with commission test only for the test samples in the case of delivering samples by clients.