


REPORT NUMBER:

SHAT07824945



TEST REPORT

Number : SHAT07824945

Applicant : HUI'AN CHISAGE INDUSTRIAL CO., LTD
NO.28, NANMACHANGXIANGWANGGAO RD,
JIANGSU

Date : Nov 29, 2023

Attn : KERRY XIE

Sample Description :

One (1) Piece Of Submitted Knitted Sample Said To Be 81% Polyester 19% Elastane Fabric With Print.
Applicant's Provided Care Instruction/Label :

-
Date Received/Date Test Started : NOV 27, 2023
Standard : -
Milestone : -
Form No. : -
Style No. : 346074-8796963-PPS
Purchase order : -
Color : DKT-L14A PURPLE/SS24
Buyer's Name : Decathlon Self-Reference
Manufacturer's Name : 60055 - HUIAN CHISAGE INDUSTRIA
Starlims Code : -
Ref. : -

Physical Tests:

Aspect Control Of Screen Print And Heat Transfer After Accelerated Ageing By Washing And Drying	See Detail
Manual Stretching Of Screen-Print Or Heat Transfer On Textile	See Detail

Prepared And Checked By:
For Intertek Testing Services Ltd., Shanghai



Connie Zhang
Technical Director

TEST REPORT

Number : SHAT07824945

Tests Conducted (As Requested By The Applicant)

- 1 Aspect Control Of Screen Print And Heat Transfer After Accelerated Ageing By Washing And Drying (Decathlon Method DS0096 Version 8, In Dynawash, 80 Minutes Wash At 60°C With Tap Water, 1 kg Total Load, With 70g ECE(B) Detergent, Spin Speed At 1000 RPM/min, Followed By 90 minutes Tumbler Dry):

Sample Is Screen-Print/ Heat Transfer

No degradation

Conclusion

No Comment

Remark :

Number Of Tested Sample: 2

- 2 Manual Stretching Of Screen-Print Or Heat Transfer On Textile (Decathlon Test Method DS-130, Version B):

Sample Is Screen-Print / Heat Transfer

Result:

Good

Conclusion

No Comment

TEST REPORT

Number : SHAT07824945

Tests Conducted (As Requested By The Applicant)



Remark : Elasticity Of The Fabric Is More Than 40%. Dynamometer Was Used.

End of Report

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.

This report shall not be reproduced except in full, without written approval of the laboratory.